



www.silexsc.com.pl

Silex S.C. Fasteners - bolts and nuts

Street Jana Matejki 6, Brzezie, 66-100 Sulechów

tel./fax.: +48 68 385 27 50

mobile: +48 512 012 110

email: biuro@silexsc.com.pl

NIP: 973-088-61-91

Regon: 080147360

Bolts chemical properties

Class properties	Material and treatment	Chemical constitution (inspection analysis) % (m/m)				Allowable temperature	
		C		P	S	B	°C
		min	max	max	max	max	min
3.6	Carbon steel	-	0,20	0,05	0,06	0,003	-
4.6		-	0,55	0,05	0,06	0,003	-
4.8							
5.6		0,13	0,55	0,05	0,06	0,003	-
5.8		-	0,55	0,05	0,06		
6.8							
8.8	Carbon steel with alloy additives (exp.B, Mn or Cr) quenched and tempered	0,15	0,40	0,035	0,035	0,003	425
	Carbon steel quenched and tempered	0,25	0,55	0,035	0,035		
9.8	Carbon steel with alloy additives (exp.B, Mn or Cr) quenched and tempered	0,15	0,35	0,035	0,035	0,003	425
	Carbon steel quenched and tempered	0,25	0,55	0,035	0,035		
10.9	Carbon steel with alloy additives (exp.B, Mn or Cr) quenched and tempered	0,15	0,35	0,035	0,035	0,003	340
10.9	Carbon steel quenched and tempered	0,25	0,55	0,035	0,035	0,003	425
	Carbon steel with alloy additives (exp.B, Mn or Cr) quenched and tempered	0,20	0,55	0,035	0,035		
	Carbon steel quenched and tempered	0,20	0,55	0,035	0,035		
12.9	Carbon steel quenched and tempered	0,28	0,50	0,035	0,035	0,003	380